

LinoWall xf² (2mm)

Datasheet

Classification	Norm	Tarkett Value
Product type	ISO 24011 (EN 548)	Approved linoleum for walls application
Technical Characteristics	Norm	Tarkett Value
Total thickness	EN ISO 24346	2 mm
Total weight	EN ISO 23997	2900 g/m ²
Surface treatment		xf ² ™
Installation method		Glue-Down
Performance for CE Marking	Norm	Tarkett Value
Declaration of Performance #	EN 15102	0200 0045 DoP 2013 07
Reaction to fire	AS/NZS 3837	TBA
Fire Effluent Toxicity	ISO 5659-2 (evaluation according to EN 45545-2 annex C)	CITg (4min) =0,06 and CITg (8min)=0,09 testing with irradiance of 50KW/m ² without pilot flame
Static Electrical Propensity	EN 1815	Antistatic (≤ 2 kV)
Thermal conductivity (in W/m•K)	EN 12524	0.11
Technical Performance	Norm	Tarkett Value
Impact Resistance	EN 259-2	Resistant to impacts - No visible burst nor crack
Chemical resistance	ISO 26987 - EN 423	Resistant to dilute acids, oils, fats, current solvents and alkalis
Colour fastness to light	ISO 105-B02	≥ 6
Odor Test Requirement of Emission Class M1	EN ISO 16000-28 i.A, VDI 4302	Meets Requirement
Spongeability, washability, lyability, brushability	EN 12956 / EN 233	Extra washable
Determination of antibacterial activity	ISO 22196	Naturally antibacterial (Bacteria mix - Ecoli and MRSA)
Sustainability performances	Norm	Tarkett Value
Phthalate - free		Yes
Recyclability through ReStart®		Recyclable
Allergy UK Seal Of Approval		Approved
Dimensions and designs		
Roll		Roll 2 x ≤16m
Number of designs available		10



The above information is subject to modification for the benefit of further improvement (12/04/2022). According to the European Regulation N°305/2011 for CE Marking, the Declarations of Performance are available on our website <https://www.tarkett.com>. Tarkett's instructions regarding installation, cleaning and maintenance should be observed. Please contact Tarkett at the address shown for the instructions.