

iQ Granit SD

Datasheet

Classification	Norm	Tarkett Value
Product type	ISO 10581	Permanently static dissipative pressed homogeneous vinyl flooring
Binder content	ISO 10581	Type I
Commercial classification	ISO 10874	34 Very Heavy
Industrial classification	ISO 10874	43 Heavy
Technical Characteristics	Norm	Tarkett Value
Surface treatment		New iQ PUR
Surface Restoration		Yes
Total thickness	ISO 24346	2 mm
Wear layer thickness	ISO 24340	2 mm
Total weight	ISO 23997	2800 g/m²
Performance for CE Marking	Norm	Tarkett Value
Declaration of Performance #	EN 14041	0019-0033-DoP-2013-07
Reaction to fire	AS/ISO 9239.1	Critical radiant flux $\geq 11 \text{ kW/m}^2$ Smoke 118%.min
Static Electrical Propensity	EN 1815	Antistatic ($\leq 2 \text{ kV}$)
Thermal resistance	EN 12667	$\sim 0,010 \text{ m}^2 \cdot \text{K/W}$
Slip resistance	EN 13893	Class DS ($\mu \geq 0,30$)
Technical Performance	Norm	Tarkett Value
Residual indentation	EN ISO 24343-1	Required value: $\leq 0,10 \text{ mm}$ Best measured value: 0,02 mm
Slip resistance	DIN 51130 AS 4586	R10 P4
Electrical Insulation	VDE0100, Part 600	$R_i \geq 5 \times 10^4 \text{ Ohms}$
Electrical resistance	ESD-approval SP method 2472	$R \leq 10^9 \text{ Ohms}$
Electrical resistance	EN 1081	$R_1 \leq 10^8 \text{ Ohms} / R_2 \leq 10^8 \text{ Ohms}$
Electrical Resistance	EN/IEC 61340-4-1, 100 V	$R \leq 10^8 \text{ Ohms}^*$
Curl resultant to heat	EN ISO 23999	$\leq 8 \text{ mm}$ for rolls
Clean room	ISO 14644-1	ISO class 4
Castor chair	ISO 4918	Suitable
Colour fastness to light	ISO 105-B02	≥ 7
Dimensional stability	EN ISO 23999	Average Measured Value : $\leq 0.40 \%$
Ease of Decontamination	ISO 8690 – DIN 25415	Excellent
Chemical resistance	ISO 26987	Excellent Resistance
Bacteria Resistance	ISO 846 Part C	Does not promote growth
Underfloor heating		Suitable (subfloor temperature maximum 27°C)
Seam Strength Average Value	EN 684	$\geq 240 \text{ N/50mm}$
Seam Strength Individual Value	EN 684	$\geq 180 \text{ N/50mm}$
Sustainability performances	Norm	Tarkett Value
Vinyl Council Australia		PVC Best Practice
Recyclability through ReStart®		Recyclable
Recycled content		25.5 %
Total VOC Emissions	EN 16516	Platinum ($\leq 10 \mu\text{g/m}^3$)
Formaldehyde emission		E1
GreenTag		Level A
HealthRATE		Platinum
Dimensions and designs		
Roll	Roll 2 x 23 m	
Number of designs available	14	

* Measured to ground



The above information is subject to modification for the benefit of further improvement (24/11/2025). According to the European Regulation N°305/2011 for CE Marking, the Declarations of Performance are available on our website <https://www.tarkett.com>. Tarkett's instructions regarding installation, cleaning and maintenance should be observed. Please contact Tarkett at the address shown for the instructions.

Tariff Bvtusbj
Tvjuf12-1Mfwf14-13 Dpivncjb!Dpvsu!Cbvn!Ibn!Ijmt,!OTX!3264
J13*19964!2311
dvtupnfstfswjdfAubslfwwdpn
xxxubslfwwdpn/bv

